



<b>DESCRIPTION</b>			
Total thickness on grain side	EN 428	mm	2.00
Wear layer thickness	EN 429	mm	1.00
Weight	EN 430	g/sq.m	2400
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
<b>CLASSIFICATION</b>			
Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
Fire rating	EN 13501-1	class	B <sub>fl</sub> -s1 (under process)
Static electrical propensity	EN 1815	kV	< 2
Slip resistance : Pendulum Test (dry & wet)	BS 7976-2	PTV	> 36
Surface roughness Rz	UK slip resistant group	µm	> 20
Slip resistance wet: ramp test with oil	DIN 51 130	class	R11
Slip resistance wet : bare foot	DIN 51 097	class	C
Slip resistance – ramp test	EN 13845 (annex C)	class	ESb
<b>PERFORMANCE</b>			
Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 4
Wear group	EN 649	group	P
Type Binder content	ISO 10582	type	I
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥6
Chemical products resistance	EN 423	-	OK
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100
<b>CE MARKING</b>			
	EN 14041	-	
		-	